

Anglo Asian Mining PLC

Table of Assay Results from Gedabek Drilling Programme

Hole No.	Type	TD (m)	From (m)	To (m)	Interval (m)	Au Eq. (g/t)	Au (g/t)	Ag (g/t)	Cu (%)
GDDD14	Core	200.0	66.0	74.2	8.2	1.56	1.14	2.85	0.16
and			74.2	76.0	1.8	Void			
and			76.0	110.0	34.0	2.14	1.10	5.27	0.41
and			116.0	124.0	8.0	2.93	1.25	10.68	0.65
GDDD15	Core	190.0	26.0	44.0	18.0	4.41	3.12	14.61	0.45
and			62.0	78.0	16.0	1.82	0.20	2.06	0.69
with			68.0	74.0	6.0				1.52
GDDD16	Core	180.0	No Intersections with AuEq grade above 0.5 g/t						
GDDD17	Core	185.0	10.0	36.0	26.0	2.18	1.32	15.12	0.27
and			42.0	62.0	20.0	1.35	0.26	2.39	0.46
with			48.0	52.0	4.0				1.35
and			66.0	78.0	12.0	0.84	0.08	1.17	0.32
GDDD18	Core	183.0	32.0	40.0	8.0	0.79	0.11	3.40	0.27
and			122.0	134.0	12.0	0.82	0.21	1.48	0.26
GDDD19	Core	See GDRC09a							
GDDD20	Core	210.0	20	26.0	6.0	1.09	0.96	4.52	0.02
and			74	80.0	6.0	0.88	0.33	2.07	0.23
GDDD21	Core	10.0 Abandoned - not assayed							
GDRC08	RC	204.0	38.0	61.0	22.0	6.17	4.91	57.58	0.13
Excluding			46.0	47.0	1.0	No Sample			
and			64.0	73.0	9.0	8.78	5.34	17.97	1.36
and			77.0	88.0	11.0	1.24	0.42	4.35	0.32
and			92.0	96.0	4.0	1.58	0.09	0.58	0.64
and			131.0	138.0	7.0	1.98	0.47	2.74	0.64
GDRC09	RC	47.0	Abandoned - not assayed						
GDRC09a									
/ GDDD19	RC / Core	89.0/223.0	0.0	3.0	3.0	0.66	0.44	6.17	0.05
and			23.0	27.0	4.0	1.00	0.91	1.82	0.03
and			32.0	49.0	17.0	3.65	2.37	14.97	0.45
GDRC10	RC	194.0	45.0	84.0	39.0	0.77	0.13	1.15	0.27
GDRC11	RC	153.0	13.0	63.0	50.0	2.83	2.40	9.79	0.12
with			16.0	22.0	6.0		7.20	34.19	
and			111.0	120.0	9.0	7.58	7.24	17.27	0.02
with			112.0	116.0	4.0		14.32	34.14	
and			143.0	146.0	3.0	1.25	1.04	3.65	0.06
GDRC12	RC	165.0	14.0	27.0	13.0	6.33	5.17	8.12	0.45
and			35.0	52.0	17.0	1.57	0.10	0.33	0.64
and			63.0	69.0	6.0	1.66	0.07	0.25	0.69
GDRC13	RC	145.0	81.0	95.0	14.0	1.33	0.05	0.32	0.55
GDRC14	RC	145.0	24.0	29.0	5.0	1.15	0.19	0.86	0.41
and			35.0	67.0	32.0	0.82	0.06	0.85	0.32
GDRC15	RC	102.0	24.0	30.0	6.0	1.47	0.22	2.10	0.53
and			36.0	56.0	20.0	0.80	0.03	0.27	0.34

Ms. L Mach of SRK Consulting has reviewed and approved the information, pertaining to Gedabek, contained in this press release for the purposes of Part Two of the "Guidance Note for Mining, Oil and Gas Companies" dated March 2006 issued by the London Stock Exchange. Ms. Mach is a Certified Professional Geologist (American Institute of Professional Geologists) and is considered a Qualified Person within the meaning of NI 43-101 and JORC. SRK Consulting is an international minerals consultancy group, independent of Anglo Asian.

Anglo Asian Mining PLC

Notes:

1. All holes are drilled vertically and reported intervals are drill-hole lengths; true widths of mineralisation intercepts have not yet been calculated.
2. The diamond drill cores are predominately HQ-sized (63.5mm diameter), with some holes reduced to NQ (47.6mm diameter). The RC holes GDRC08 to GDRC09a are 115mm in diameter and later holes are 135mm.
3. The core is split on-site and one half is shipped to OMAC Laboratories Ltd in Loughrea, Ireland. RC chips are reduced to a nominal 2 kilogram sample on-site and also sent to OMAC. Gold is analysed by fire assay (30 gram) with atomic absorption finish. Copper and silver are analysed with a 46 element ICP procedure. A laboratory quality assurance/quality control programme is in place with blanks and duplicate samples inserted into the sample stream. External check assays will be done at ALS Chemex in Vancouver, British Columbia, Canada.